

FOI 090 "24924860

Sub
A258

I claim:

1. A golf ball comprising:
a core;
an inner cover layer disposed on said core, said inner cover layer
5 having a Shore D hardness of at least 60, said inner cover layer comprising a
blend of two or more low acid ionomer resins, each containing no more than 16%
by weight of an alpha, beta-unsaturated carboxylic acid; and
an outer cover layer disposed on said inner cover layer, said outer
cover layer having a Shore D hardness of from about 55 to about 59, a thickness
10 of from about 0.01 to about 0.07 inches, and comprising a polyurethane material.

2. The golf ball of claim 1 wherein said outer cover exhibits a Shore D
hardness of from about 56 to about 58.

3. The golf ball of claim 1 wherein said outer cover exhibits a Shore D
hardness of about 57.

4. ² The golf ball of claim 1 wherein said outer cover layer has a
thickness of from about 0.01 to about 0.05 inches.

5. ³ The golf ball of claim 1 wherein said outer cover layer has a
thickness of from about 0.03 to about 0.06 inches.

Sub
A259

6. A golf ball comprising:
a core;
an inner cover layer disposed about said core, said inner cover layer
having a Shore D hardness of at least 60, said inner cover layer comprising a
5 blend of two or more low acid ionomer resins, each containing no more than 16%
by weight of an alpha, beta-unsaturated carboxylic acid; and
an outer cover layer disposed on said inner cover layer, said outer
cover layer having a Shore D hardness of from about 60 to about 68, a thickness
of from about 0.01 to about 0.07 inches, and comprising a polyurethane material.

7. The golf ball of claim 6 wherein said outer cover exhibits a Shore D hardness of from about 62 to about 66.

8. The golf ball of claim 6 wherein said outer cover exhibits a Shore D hardness of from about 63 to about 64.

9. The golf ball of claim 6 wherein said outer cover layer has a thickness of from about 0.01 to about 0.05 inches.

10. The golf ball of claim 6 wherein said outer cover layer has a thickness of from about 0.03 to about 0.06 inches.

11. A golf ball comprising:
a core;
an inner cover layer disposed on said core, said inner cover layer having a Shore D hardness of about 60 or more, said inner cover layer comprising an ionomeric resin including no more than 16% by weight of an alpha, beta-unsaturated carboxylic acid and having a modulus of from about 15,000 to about 70,000 psi; and
an outer cover layer disposed about said inner cover layer, said outer cover layer having a Shore D hardness of from about 55 to about 68, a thickness of from about 0.01 to about 0.07 inches, and comprising a polyurethane material.

12. The golf ball of claim 11 wherein said outer cover exhibits a Shore D hardness of from about 56 to about 58.

13. The golf ball of claim 11 wherein said outer cover exhibits a Shore D hardness of about 57.

14. The golf ball of claim 11 wherein said outer cover exhibits a Shore D hardness of from about 62 to about 66.

Sub
A32

15. The golf ball of claim 11 wherein said outer cover exhibits a Shore D hardness of from about 63 to about 64.

16.¹⁰ The golf ball of claim 11⁸ wherein said outer cover layer has a thickness of from about 0.01 to about 0.05 inches.

17.¹¹ The golf ball of claim 11⁸ wherein said outer cover layer has a thickness of from about 0.03 to about 0.06 inches.

09873642 060401